

## PP & PE Fibres - Textile Grade Range

GRADE NAME		MFR [g/ 10'] 230°C/2,16 kg	ADDITIVATION	FEATURES/APPLICATION
<b>Polypropylene Strapping - Tapes - Monofilament</b>				
<i>Adflex</i>	Q100F	0.6		Strapping
<i>Moplen</i>	HP556E	0.8	low WCO	Strapping
<i>Moplen</i>	HP450H	1.8	low WCO	Strapping, Tapes, Monofilaments
<i>Moplen</i>	HP456H	1.8	low WCO	Strapping, Tapes, Ropes, Monofilaments
<i>Moplen</i>	HP456J	3.4	low WCO	Strapping, Tapes, Monofilaments
<b>Polypropylene Staple Fibres - CF/BCF</b>				
<i>Moplen</i>	HP452J	3.4	AGF	Staple Fibres
<i>Moplen</i>	HP552K	4	AGF	Staple Fibres
<i>Moplen</i>	HP552L	6	AGF	Staple Fibres
<i>Moplen</i>	HP554M	11.5	AGF	Thermal-Bonding Staple Fibres
<i>Moplen</i>	HP552N	13	AGF	Staple Fibres, CF
<i>Moplen</i>	HP552R	25	AGF	Staple Fibres, CF/BCF
<i>Adflex</i>	Z101H	27	AGF	in-blend for enhanced softness
<i>Moplen</i>	RP261S	30	AGF	Soft filaments
<b>Polypropylene Spunbond - POY - HTY</b>				
<i>Moplen</i>	HP561N	12	AGF	narrow MWD for Spunbond, High-Tenacity
<i>Moplen</i>	PP567P	18	AGF	narrow MWD for Spunbond, CF/BCF
<i>Moplen</i>	HP561R	25	AGF	narrow MWD for Spunbond, HTY
<i>Adflex</i>	Z101H	27	AGF	in-blend for enhanced softness
<i>Moplen</i>	RP261S	30	AGF	Soft filaments
<i>Moplen</i>	HP561S	32	AGF	narrow MWD for Spunbond, POY
<i>Moplen</i>	HP561S HP	36	AGF	narrow MWD for Spunbond, POY
<b>Polypropylene Meltblown</b>				
<i>Moplen</i>	HP560W	450		very narrow MWD
<i>Moplen</i>	HP560X	800		very narrow MWD
<i>Moplen</i>	HP560Y	1200		very narrow MWD
<i>Moplen</i>	HP560Z	1500		very narrow MWD

AGF - Anti-Gas Fading

BCF/ CF - Bulk Continuous/Continuous Filament

HTY - High Tenacity Yarn

MWD - Molecular Weight Distribution

POY - Partially Oriented Yarn

WCO - Water Carry Over

GRADE NAME		MFR [g/ 10'] 190°C / 5 kg	MFR [g/ 10'] 190°C /21,6 kg	FRR 21,6 kg/ 5 kg	Density g/cm <sup>3</sup>	Additivition	Features/Application
<b>High Density Polyethylene</b>							
<i>Hostalen</i>	ACP 7740 F1	1.8	18	10	0.948	Lubricant	narrow MWD, Tubular nets, Slit films & tapes, Various nets
<i>Hostalen</i>	ACP 7740 F2	1.8	18	10	0.948		narrow MWD, Slit films & tapes, Various nets
<i>Hostalen</i>	GF 7740 F2	1.8	23	13	0.946		Slit films & tapes, Various nets
<i>Hostalen</i>	ACP 7740 F3	1.6	16	10	0.946		narrow MWD, Round Bale Nets
<i>Hostalen</i>	GF 7750 M2	3.3	33	10	0.957	Lubricant	Monofilament, various nets
<i>Hostalen</i>	GF 7750 M3	1.7	18	11	0.957	Lubricant	High tenacity monofilaments, Various nets

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product.

*Adflex, Hostalen, Hostalen ACP, Moplen*, are trademarks owned and/or used by the LyondellBasell family of companies.