

# High-Performance Polyolefin and Styrenic Compounds for Extrusion and Thermoforming Applications



## A Premium Surface Finish

Your customers won't worry about chips and scratches when you use LyondellBasell's enhanced polyolefin and styrenic compounds. Our innovative solutions enable paintable and paint-free applications that look as good as they last – even in the harshest outdoor environments. And last they will, with fade-resistant color retention and stain resistance, combined with a strength that goes right through to the core.

The flexibility and the versatility of these remarkable materials make them a cost-effective replacement for many traditional materials, allowing you to differentiate and customize your applications.

## The Secret Is in the Science

These weatherable polymers are the future of surface finish technology and an innovative approach to Class "A" decorative surfaces. This patented thermoplastic olefin technology is suitable for a variety of processes, including thermoforming, film and sheet extrusion, and profile extrusion. Parts formed from these resins exhibit high resistance to bubbling, chipping, staining and fading and provide superior color and product protection.

These materials are based on TPO, ASA, ASA/PC and ASA/AES polymers and offer a broad range of engineered properties that can be customized for your unique application needs. They offer exceptional UV resistance, lasting durability, extreme toughness, paintability and excellent color retention, and they are available in a broad range of gloss levels and custom colors.

## Your Materials of Choice

LyondellBasell's polyolefin and styrenic compounds offer superior advantages over conventional materials including painted metal or plastic, laminated paint films, acrylic laminates and coatings:

- High-quality appearance with mold-in-color technology and paintable applications for class "A" finishes
- No chipping or cracking – even in extreme temperatures or high-stretch thermoforming processes
- Process versatility
- Customized color and color-matching
- Cost-effective performance
- Recyclability



## Enhanced Polyolefin and Styrenic Polymer Systems

### Markets/Applications



#### Agriculture and Heavy Equipment

Resistance to fading from environmental exposure, as well as protection from fertilizers, pesticides and other chemicals, make these polymers perfect for combines, tractors and other large farm machinery. Another added benefit is a higher tolerance toward cracking under vibrational loads. Enhanced polyolefins can be applied to a variety of applications including roof, hood, fender and other body panels.



#### RV, Heavy Truck and Bus

Enhanced polyolefins are suitable for large transportation applications such as heavy trucks, buses and RVs. Side and roof panels, bumper covers, fender skirts, AC shrouds, propane tank covers, nose cones and interior decorative finishes are just some of the many applications in this market.



#### Power Sports

Snowmobiles, ATVs, jet skis and motorcycles are all perfect applications for enhanced polyolefins which are not only impact-resistant, flexible, durable and ductile under sub-zero temperatures but also lightweight and fade-resistant. Side panels, wheel covers, hood panels and other areas are a great fit for these polymers.



#### Industrial Components

Stiffness, ductility and resistance to weather, chemicals, stress and vibrational cracking make enhanced polyolefins ideal for shrouds, housings and panels in high abuse environments.



#### Personal Watercraft

Power and pontoon boats along with kayaks all benefit from enhanced polyolefins which are lightweight, durable and can withstand constant environmental exposure. Applications can range from interior consoles and headliners to rail skirts and storage compartments.



#### Lawn and Garden

Personal use lawn and garden equipment, such as mowers and garden tractors, gains added resistance from chipping, cracking and bubbling by using enhanced polyolefins. These polymers are ideal for applications like wheel wells, vehicle hoods and body panels.



#### Automobile

Enhanced polyolefins with impact resistance, extreme durability, flexibility and ductility are the superior material for exterior and interior auto applications. LyondellBasell's Color Technology Center has the capability to match a variety of colors in the auto market and provides a wide selection from solids to pearlescent and metallic. Applications include bumper fascias, rocker panels and other decorative finishes.

## Select the LyondellBasell Capstock Grade That's Right for You

These capstock resins provide many exciting benefits in performance and appearance with a broad range of gloss levels depending on your application requirements



		Capstock Grades					
		Polytrope STR	Polytrope STR	Indure	Polytrope STR	HIFAX	
Properties	Method	Units	3035EU-01UV Natural	3571EU-01 UV Natural	E1500HG UV NAT	3566EU-01 UV Natural	
<b>GENERAL</b>							
Melt Flow Rate (230°C, 2.16 kg)	ISO 1133	g/10 min	0.4	3.9	2.0	2.5	
Specific Gravity	ISO 1183	--	1.06	0.92	0.90	0.91	
Hardness	ISO 868	Shore D	74	70	70	74	
<b>THERMAL</b>							
Heat Deflection Temperature	ISO 75						
@ 0.45 MPa		°C	75	76	72	77	
@ 1.80 MPa		°C	50	50	48	50	
<b>MECHANICAL</b>							
Flexural Modulus	ISO 178	MPa	1900	750	1014	1000	
Tensile Yield Strength	ISO 527	MPa	24	21	30	24	
Tensile Elongation at Break	ISO 527	%	410	510	500	500	
Gloss Gardner Gloss, 60°, Smooth Sheet, After Forming			2-10	<20	85-95	85-95	
		<b>Key Attributes</b>	Durable, Low Gloss, Hard Mar Resistant Surface	Excellent Clarity, Low Gloss, Durable	High Gloss Polyolefinic Cap Layer	High Clarity, Gloss, Improved Durability, Non-Blush	Cap Layer To Promote Reduced Stress Whitening

# Select the LyondellBasell TPO Grade That's Right for You



Offering a broad product portfolio that has been designed to meet property performance balance through a diverse offering of stiffness, impact and thermal expansion properties

		Sheet Extrusion Grades										
Properties	Method	Units	Polytrope STR	Polytrope STR	Sequel	Sequel	Sequel	Polytrope STR	Polytrope STR	Polytrope STR	Polytrope STR	
			1025 UV Natural	1026EU-01 UV Natural	E3400 UV NAT	E3400 NON UV NAT	E3200 UV NAT	E3200 NON UV NAT	1050EU-01 UV Natural	1050EP-01 NON UV Natural	1060EU-01 UV Natural	
<b>GENERAL</b>												
Melt Flow Rate (230°C, 2.16 kg)	ISO 1133	g/10 min	1	0.7	0.7	0.65	0.75	0.75	0.5	0.5	0.7	
Specific Gravity	ISO 1183	--	0.99	0.99	1.12	1.12	1.08	1.08	1.14	1.14	1.16	
Hardness	ISO 868	Shore D	71	71	67	66	66	66	68	68	70	
Flame rating type, all colors		Internal	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	HB @ 0.125 in	
<b>THERMAL</b>												
Heat Deflection Temperature @ 0.45 MPa	ISO 75	°C	94	98	102	95	85	85	114	114	117	
@ 1.80 MPa		°C	54	54	56	52	49	49	57	57	57	
CLTE (-30°C to 80°C)	ASTM E228	10 <sup>-5</sup> /°C	9.9		4.8	4.0	5.5	5.5	4.0	4.0	5.4	
<b>MECHANICAL</b>												
Flexural Modulus	ISO 178	MPa	1,725	1,650	2,100	2,100	1,450	1,450	2,400	2,400	3,000	
Tensile Yield Strength	ISO 527	MPa	21	26	21	22	21	21	24	24	27	
Tensile Elongation at Break	ISO 527	%	>200	>500	>200	>500	>500	>500	300	300	175	
<b>IMPACT</b>												
Izod Impact Strength @ 23°C (73°F)	ISO 180	kJ/m <sup>2</sup>	82	54	82	64	67	67				
@ -30°C (-22°F)		kJ/m <sup>2</sup>	7	4	7	6.5	4.8	4.8				
Multi-Axial Impact (2.2 m/s) -15°C	ASTM D3763	J		17	51	48	40	40	44	44		
Total Energy		D/B		100% brittle	100% ductile	100% ductile	partially ductile	partially ductile	100% ductile	100% ductile		
Multi-Axial Impact (2.2 m/s) -30°C	ASTM D3763	J	47.4		57	39	28	28				
Total Energy		D/B	100% D		100% ductile	100% ductile	brittle	brittle				
Failure Mode (D-Ductile; B-Brittle)												
<b>Key Attributes</b>			For Applications requiring lower stiffness and high impact.	For applications requiring lower stiffness. Commercially approved for Automotive trim applications.	Excellent balance of high stiffness and high impact; improved melt strength for thermoforming.	Excellent balance of high stiffness and high impact; improved melt strength for thermoforming.	Adjusted for cost sensitive applications requiring less impact and Thermoformability.	Adjusted for cost sensitive applications requiring less impact and Thermoformability listed. Modified for full paint applications.	Designed for High Modulus and Toughness	Designed for High Modulus and Toughness, Modified for Full paint applications	Balances toughness and exceptional high stiffness and Low Temperature impact.	

# Select the Flame Retardant System That's Right for You

Our broad portfolio of PP Based polymers can be customized to fit your sheet extrusion and thermoforming processes



Properties		Flame Retardant Grades					
		TBD V2 V2 TPO (In development)	Sequel E3400FR NAT V1 TPO	Matrixx 14N2006 VO TPO	Polytrope STR 2030 NAT VO TPO	Matrixx 14N5003 VO TPO	
ASTM Standard	Units						
<b>GENERAL</b>							
Melt Flow Rate (230°C, 2.16 kg)	g/10 min	ISO 1133	1.5	0.87	1.4	0.7	12 (13.8)
Specific Gravity	g/cm3	ISO 1183	0.98	1.26	1.00	1.31	1.00
<b>THERMAL</b>							
Heat Deflection Temperature under Load, Unannealed		ISO 75					
@ 0.45 MPa	°C	ISO 75	100	103		91	85
@ 1.80 MPa	°C	ISO 75		56			
CLTE (-30°C to 80°C)	10 <sup>-5</sup> /°C	ASTM E228		5.3		5.4	
<b>MECHANICAL</b>							
Flexural Modulus	MPa	ISO 178	1700	2240	1240	2,100	1210 (1181)
Tensile Yield Strength	MPa	ISO 527	25	20	(24.1)	19	24 (23.3)
Tensile Elongation at Break	%	ISO 527	10	>150	(500)	430	(300)
<b>IMPACT</b>							
Izod Notched Impact Strength		ISO 180					
@ 23°C (73°F)	kJ/m2		>4.0	38.0			
@ 23°C (73°F)	ft/lb- J/m				15 ftlb/in& 800 j/m	8 ftlb/in& 430 j/m	2.5 ftlb/in& 130 j/m
@ -30°C (-22°F)	kJ/m2			4.0			(2 ftlbs/in)
@ -30°C (-22°F)	ft/lb- J/m					.6 ftlb/in& 32j/m	
Multi-Axial Impact (2.2 m/s) -15°C		ASTM D3763					
Total Energy	J			26	35	35	
Failure Mode (D-Ductile; B-Brittle)	D/B			Partially ductile	100% ductile	Partially ductile	
Multi-Axial Impact (2.2 m/s) -30°C		ASTM D3763					
Total Energy	J			37			
Failure Mode (D-Ductile; B-Brittle)	D/B			Brittle			
<b>FLAME RATING TYPE</b>							
All Colors	UL		V2 @3MM	V1 @ 3.0 mm. V0 @ 6.0MM	V0 @ 3.0 MM (V-0 @ 1.5mm)	V0 @ 1.5mm & 3MM - 5VA @ 3.0 MM	1.5MM V-0 3. MM V-0
		<b>Key Attributes</b>	For applications requiring UL 94 V-2 flame retardancy.	For applications requiring UL 94 V-1 flame retardancy.	For applications requiring UL 94 V-0 flame retardancy.	For applications requiring UL 94 V-0 flame retardancy.	For Injection Molding applications requiring V-0 Flame retardancy for use as extruded part accessories.

## Select the Weatherable Polymer Systems That's Right for You



Our broad portfolio of ABS, ASA, ASA/PC and ASA/AES polymers can be customized to fit your sheet extrusion and thermoforming processes

Properties	ASTM Standard	Units	Conditions	Co-Extrusion Sheet Grades					
				Centrex 485 CS	Centrex 825A	Centrex 833A	Centrex ST4800	Diamond 9501-1001S	Diamond ABS 9501
<b>GENERAL</b>									
Resin Type				ASA - Low Gloss	ASA - High Gloss	ASA / AES	ASA / TPE		
Melt Flow Rate	D 1238	g/10 min	200°C, 5 kg	N/A	N/A	N/A	N/A	0.40 to 1.2.g/10 min	0.40 g/10 min
Melt Flow Rate	D 1238	g/10 min	220°C, 10 kg	5	12	10	N/A	N/A	N/A
Melt Flow Rate	D 1238	g/10 min	230°C, 3.8 kg	1.5	3.5	1.8	15	N/A	N/A
<b>THERMAL</b>									
Vicat	D 1525	°F	1 kg, 120°C/hr	212	215	195	N/A	221	284
Deflection Temperature under Load, Unannealed	D 648	°F	66 psi, 0.125"	188	198	185	N/A	195	253
Deflection Temperature under Load, Unannealed	D 648	°F	264 psi, 0.125"	155	172	160	N/A	168	223
<b>MECHANICAL</b>									
Tensile Modulus	D 638	psi	73°F, 0.2 in/min	210,000	330,000	295,000	N/A	N/A	N/A
Tensile Stress at Yield	D 638	psi	73°F, 0.2 in/min	3,850	6,400	5,100	N/A	6,240	6,070
Tensile Stress at Break	D 638	psi	73°F, 0.2 in/min	2,285	4,800	4,100	N/A	4,930	N/A
Tensile Elongation at Break	D 638	%	73°F, 0.2 in/min	50	36	35	N/A	20	N/A
Flexural Modulus	D 790	psi	73°F, 0.05 in/min	200,000	305,000	250,000	N/A	333,000	317,000
Flexural Stress at Yield	D 790	psi	73°F, 0.05 in/min	50,600	7,800	7,500	N/A	N/A	N/A
<b>IMPACT</b>									
Izod Notched Impact Strength	D 256	ft - lb/in	73°F, 0.125"	2.5	2.5	9	N/A	9.7	2.9
Hardness	D 785	scale		97 R	104 R	89 R	46 D	101	104
Instrumented Impact, Total Energy	D 3763	joules	73°F, 0.125"	24	38	43	8	N/A	N/A
Instrumented Impact, Total Energy	D 3763	joules	-30°F	6	12	30	N/A	N/A	N/A
Specific Gravity	D 792		23°C	1.06	1.05	1.05	1.08	1.04	1.07
Gloss, Sheet/Profile*	D 523		60°	20	95	95	10	N/A	N/A
Gloss, Formed Sheet*	D 523		60°	10	90	90	8	N/A	N/A
<b>Key Attributes</b>				Low Gloss 10 @ at 60 degrees	High Gloss 90+ @ at 60 degrees	High Gloss 90+ @ at 60 degrees	Low Gloss 10 @ at 60 degrees	Ultra High Impact Resistance	Ultra High Impact Resistance

# ABOUT US

We are LyondellBasell – a leader in the global chemical industry creating solutions for everyday sustainable living. Through advanced technology and focused investments, we are enabling a circular and low carbon economy. Across all we do, we aim to unlock value for our customers, investors and society. As one of the world's largest producers of polymers and a leader in polyolefin technologies, we develop, manufacture and market high-quality and innovative products for applications ranging from sustainable transportation and food safety to clean water and quality healthcare. For more information, please visit [www.lyondellbasell.com](http://www.lyondellbasell.com) or follow [@LyondellBasell](https://www.linkedin.com/company/lyondellbasell) on LinkedIn.

Before using a product sold by a company of the LyondellBasell family of companies ("LyondellBasell"), users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. LyondellBasell MAKES NO WARRANTY, EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS AGREED TO BY LyondellBasell IN THE PRODUCT SALE CONTRACT.

LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product.

*Polytrope, Sequel, Hifax, Polytrope STR, Centrex and Diamond* are trademark owned and/or used by the LyondellBasell family of companies and they are registered in the U.S. Patent and Trademark Office.