

## Test Report

SPONSOR: **TURF Design Inc.**  
Elgin, IL

Sound Absorption  
**RAL™-A20-404**

CONDUCTED: 2020-09-17

Page 1 of 8

ON: Block (LG) baffle (9 objects spaced 10 in. on center)

### TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

### INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as Block (LG) baffle (9 objects spaced 10 in. on center). The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

#### Product Under Test

Trade Name: Block (LG)  
Material: Polyethylene terephthalate felt  
Manufacturer: TURF Design Inc.

### SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

#### Test Specimen

Material: Notched and folded semirigid felt paneling  
Dimensions: 9 @ 138.1 mm (5.44 in.) wide by 2438 mm (96 in.) long  
Thickness: 138.1 mm (5.44 in.)  
Overall Weight: 23.93 kg (52.75 lbs)

## Test Report

TURF Design Inc.  
2020-09-17

**RAL™-A20-404**  
Page 2 of 8

### Physical Measurements (per object)

Dimensions: 0.14 m (5.437 in) wide by 2.44 m (96.0 in) long  
Thickness: 0.14 m (5.437 in)  
Weight: 2.66 kg (5.86 lbs)

### Test Environment

Room Volume: 291.98 m<sup>3</sup>  
Temperature: 22.3 °C ± 0.1 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)  
Relative Humidity: 59.0 % ± 0.2 % (Requirement: ≥ 40 % and ≤ 5 % change)  
Barometric Pressure: 99.2 kPa (Requirement not defined)

Each sound absorbing object had an absorptive area (all exposed surfaces) of 1.39 m<sup>2</sup> (14.91 ft<sup>2</sup>). The total absorptive area (all exposed surfaces) of all sound-absorbing objects was 12.47 m<sup>2</sup> (134.20 ft<sup>2</sup>). The array of objects covered 5.30 m<sup>2</sup> (57 ft<sup>2</sup>) of the horizontal test surface (total treated area).

### MOUNTING METHOD

Type J Mounting: The specimen is an array of 9 spaced sound absorbing baffles suspended from cables such that the closest face of the baffles is located approximately 1.37 m (53.75 in.) from the horizontal test surface. This approximates the mounting method of a typical ceiling baffle installation. The baffles were evenly distributed in a single row, spaced 254 mm (10 in.) on center.

## Test Report

**TURF Design Inc.**  
2020-09-17

**RAL™-A20-404**  
Page 3 of 8



Figure 1 – Specimen mounted in test chamber



Figure 2 – Detail of specimen material

## Test Report

**TURF Design Inc.**  
2020-09-17

**RAL™-A20-404**  
Page 4 of 8




Figure 3 – Underside of individual baffle

## Test Report

**TURF Design Inc.**  
2020-09-17

**RAL™-A20-404**  
Page 5 of 8


### TEST RESULTS

Note: There is currently no standardized method for calculating Absorption Coefficients from spaced object absorbers. The sound absorption performance of spaced object absorbers should not be compared directly with specimens tested as a single rectangular area (e.g. mounting types A, E, etc.).

1/3 Octave Center Frequency (Hz)	Total Absorption		Absorption per Object	
	(m <sup>2</sup> )	(Sabins)	(m <sup>2</sup> / Object)	(Sabins / Object)
100	1.64	17.70	0.18	1.97
** 125	1.42	15.34	0.16	1.70
160	1.71	18.39	0.19	2.04
200	3.01	32.35	0.33	3.59
** 250	3.66	39.43	0.41	4.38
315	4.92	52.92	0.55	5.88
400	5.75	61.90	0.64	6.88
** 500	6.73	72.41	0.75	8.05
630	7.47	80.42	0.83	8.94
800	7.73	83.23	0.86	9.25
** 1000	7.72	83.06	0.86	9.23
1250	7.78	83.77	0.86	9.31
1600	8.35	89.84	0.93	9.98
** 2000	9.44	101.60	1.05	11.29
2500	9.75	104.93	1.08	11.66
3150	10.12	108.93	1.12	12.10
** 4000	10.29	110.71	1.14	12.30
5000	10.63	114.46	1.18	12.72

Tested by   
Marc Sciaky  
Senior Experimentalist

Report by   
Malcolm Kelly  
Test Engineer, Acoustician


Approved by   
Eric P. Wolfram  
Laboratory Manager



TURF Design Inc.  
2020-09-17

**RAL™-A20-404**  
Page 6 of 8

**SOUND ABSORPTION REPORT**  
Block (LG) baffle (9 objects spaced 10 in. on center)



## Test Report

**TURF Design Inc.**  
2020-09-17

**RAL™-A20-404**  
Page 7 of 8

### APPENDIX A: Extended Frequency Range Data

Specimen: Block (LG) baffle (9 objects spaced 10 in. on center) (See Full Report)

*The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.*

1/3 Octave Band Center Frequency (Hz)	Total Absorption		Absorption per Object	
	(m <sup>2</sup> )	(Sabins)	(m <sup>2</sup> / Object)	(Sabins / Object)
31.5	0.96	10.29	0.11	1.14
40	-0.43	-4.61	-0.05	-0.51
50	-0.16	-1.77	-0.02	-0.20
63	0.39	4.19	0.04	0.47
80	0.94	10.11	0.10	1.12
100	1.64	17.70	0.18	1.97
125	1.42	15.34	0.16	1.70
160	1.71	18.39	0.19	2.04
200	3.01	32.35	0.33	3.59
250	3.66	39.43	0.41	4.38
315	4.92	52.92	0.55	5.88
400	5.75	61.90	0.64	6.88
500	6.73	72.41	0.75	8.05
630	7.47	80.42	0.83	8.94
800	7.73	83.23	0.86	9.25
1000	7.72	83.06	0.86	9.23
1250	7.78	83.77	0.86	9.31
1600	8.35	89.84	0.93	9.98
2000	9.44	101.60	1.05	11.29
2500	9.75	104.93	1.08	11.66
3150	10.12	108.93	1.12	12.10
4000	10.29	110.71	1.14	12.30
5000	10.63	114.46	1.18	12.72
6300	10.77	115.91	1.20	12.88
8000	10.75	115.69	1.19	12.85
10000	10.92	117.56	1.21	13.06
12500	11.31	121.73	1.26	13.53

**Test Report****TURF Design Inc.**  
2020-09-17**RAL™-A20-404**  
Page 8 of 8**APPENDIX B: Instruments of Traceability**

Specimen: Block (LG) baffle (9 objects spaced 10 in. on center) (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2020-06-26	2021-06-26
Bruel & Kjaer Mic And Preamp A	Type 4943-B-001	2311428	2019-09-27	2020-09-27
Bruel & Kjaer Sound Level Calibrator	Type 4230	861609	2019-11-19	2020-11-19
Omega Digital Temp., Humid. And Pressure Recorder	OM-CP-PRHTemp2000	P97844	2020-02-18	2021-02-18

**APPENDIX C: Revisions to Original Test Report**

Specimen: Block (LG) baffle (9 objects spaced 10 in. on center) (See Full Report)

<u>Date</u>	<u>Revision</u>
2020-09-22	Original report issued

---

END



SPONSOR: **TURF Design Inc.**  
Elgin, IL

Report Referenced: **RAL™-A20-404**  
Page 1 of 2

CONDUCTED: 2020-09-17

ON: Block (LG) baffle (9 objects spaced 10 in. on center) (See Full Test Report for Details)

#### **Appendix D to ASTM C423 Sound Absorption Test**

Non-standard calculation of equivalent NRC Rating and Absorption Coefficients from spaced absorbers

At this time ASTM C423 does not provide a standard method for determining absorption coefficients of spaced object absorbers. Tests of a set of sound absorbing objects spaced apart from each other will yield higher absorption rates than a specimen joined together as a single patch (A-Mount or E-Mount). For this reason it is unfair to provide NRC or absorption coefficient ratings for specimens that consist of a spaced set of absorbers. Despite this, the architectural industry has expressed great demand for a simple "single number" rating for these treatments. Likewise, acoustical consultants desire equivalent absorption coefficient data for use in acoustical modeling software. The following is an attempt to appease these demands until ASTM develops a standard method for calculation. Several alternate non-standard calculation methods are provided. Riverbank Acoustical Laboratories prefers method 1.

##### **Method 1) Apparent Sound Absorption Coefficient calculated from total test surface area covered**

The total sound absorption yielded by the specimen is divided by the total surface area of the test surface covered by the suspended baffles, including intermediate spaces. The baffle rigging covered 5.30 m<sup>2</sup> (57 ft<sup>2</sup>) of horizontal test surface area. With an extra 115.82 mm (4.56 in.) of width to account for the space between the tested array and what would be the next baffle in a larger array, the surface area comes to 5.58 m<sup>2</sup> (60.04 ft<sup>2</sup>). Apparent Noise Reduction Coefficient (NRC) rating and Sound Absorption Average (SAA) figures are calculated from this data based on the methods described in ASTM C423-17. This may be the most accurate method for comparing baffle arrays to ceiling tile products. The apparent sound absorption coefficient data can be assigned to a single horizontal surface or plane in acoustical modeling software for approximation of baffle array performance. Such approximations rely on the assumptions that baffle spacing is similar to that of the tested array across the entire surface and that the installation occurs over a perfectly reflective surface material.

##### **Method 2) Apparent Sound Absorption Coefficient calculated from total exposed surface area of specimen**

The total sound absorption yielded by the specimen is divided by the total surface area of all exposed specimen faces (1.39 m<sup>2</sup> (14.91 ft<sup>2</sup>) per baffle x 9 baffles = 12.47 m<sup>2</sup> (134.20 ft<sup>2</sup>) total surface area). Apparent Noise Reduction Coefficient (NRC) rating and Sound Absorption Average (SAA) figures are calculated from this data based on the methods described in ASTM C423-17. This method shows the actual absorption occurring at the exposed surfaces, but does not provide a fair comparison with materials mounted as a uniform patch (in A-mount or E-mount).

##### **Method 3) Apparent Sound Absorption Coefficient calculated from one face per baffle**

The total sound absorption yielded by the specimen is divided by the surface area of one side of one large face for each baffle in the specimen (0.337 m<sup>2</sup> (3.63 ft<sup>2</sup>) per baffle x 9 baffles = 3.03 m<sup>2</sup> (32.63 ft<sup>2</sup>) total surface area). Apparent Noise Reduction Coefficient (NRC) rating and Sound Absorption Average (SAA) figures are calculated from this data based on the methods described in ASTM C423-17. This method is favored by some material manufacturers since it yields very high NRC figures, but does not provide a fair comparison with other ceiling tile or wall panel products. Riverbank Acoustical Laboratories recommends that results obtained from this method be used for research and comparison purposes only; such results should not be used for marketed claims of product performance.

SPONSOR: **TURF Design Inc.**  
CONDUCTED: 2020-09-17

Report Referenced: **RAL™-A20-404**

Page 2 of 2

**Appendix D: Data** Note: See full test report for details of mounting position, spacing, and configuration, as these parameters greatly affect sound absorption performance.

Specimen Absorption			Method 1	Method 2	Method 3
Freq. (Hz)	Sabins	Sabins / Object	Apparent Abs. Coefficient From Total Coverage Area	Apparent Abs. Coefficient From Total Exposed Surface Area	Apparent Abs. Coefficient From One Face/Baffle
31.5	10.29	1.14	0.17	0.08	0.32
40	-4.61	-0.51	-0.08	-0.03	-0.14
50	-1.77	-0.20	-0.03	-0.01	-0.05
<b>63</b>	4.19	0.47	0.07	0.03	0.13
80	10.11	1.12	0.17	0.08	0.31
100	17.70	1.97	0.29	0.13	0.54
<b>125</b>	15.34	1.70	0.26	0.11	0.47
160	18.39	2.04	0.31	0.14	0.56
200	32.35	3.59	0.54	0.24	0.99
<b>250</b>	39.43	4.38	0.66	0.29	1.21
315	52.92	5.88	0.88	0.39	1.62
400	61.90	6.88	1.03	0.46	1.90
<b>500</b>	72.41	8.05	1.21	0.54	2.22
630	80.42	8.94	1.34	0.60	2.46
800	83.23	9.25	1.39	0.62	2.55
<b>1,000</b>	83.06	9.23	1.38	0.62	2.55
1,250	83.77	9.31	1.40	0.62	2.57
1,600	89.84	9.98	1.50	0.67	2.75
<b>2,000</b>	101.60	11.29	1.69	0.76	3.11
2,500	104.93	11.66	1.75	0.78	3.22
3,150	108.93	12.10	1.81	0.81	3.34
<b>4,000</b>	110.71	12.30	1.84	0.82	3.39
5,000	114.46	12.72	1.91	0.85	3.51
6,300	115.91	12.88	1.93	0.86	3.55
<b>8,000</b>	115.69	12.85	1.93	0.86	3.55
10,000	117.56	13.06	1.96	0.88	3.60
12,500	121.73	13.53	2.03	0.91	3.73
Apparent NRC:			<b>1.25</b>	<b>0.55</b>	<b>2.25</b>
Apparent SAA:			<b>1.23</b>	<b>0.55</b>	<b>2.26</b>

Prepared by

  
Keith Kimberling  
Test Engineer, Acoustician