1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

FOR: TURF

An MALION Technical Center

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

Test Report

Sound Absorption

Elgin, IL

CONDUCTED: 2019-01-25

RALTM-A19-036

ON: Switchblade AF over fissured ceiling tiles

Page 1 of 9

TEST METHOD

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2005 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-17: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-16: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request.

DESCRIPTION OF THE SPECIMEN

The test specimen was designated by the manufacturer as Switchblade AF over fissured ceiling tiles. A full external visual inspection performed on the test specimen by Riverbank personnel verified the manufacturer's description.

Test Specimen (in order of installation)

Layer 1

Materials: Fissured ceiling tile, wet-formed mineral fiber substrate Dimensions: 8 @ 1212.85 mm (47.75 in.) x 603.25 mm (23.75 in.)

2 @ 1212.85 mm (47.75 in.) x 330.2 mm (13 in.)

Thickness: 14.27 mm (0.562 in.) Overall Weight: 20.3 kg (44.75 lbs)

Layer 2

Trade Name: Switchblade

Material ID: AF

Materials: Polyethylene terephthalate felt

Tile Dimensions: 28 @ 598 mm (23.543 in.) x 28.7 mm (1.13 in.)

3 @ 295.27 mm (11.625 in.) x 28.7 mm (1.13 in.)

Key Geometry: Center felt piece @ 9 mm (0.354 in.) thick x 49 mm (1.929 in.) deep

9 mm (0.354 in.) thick felt adhered to both sides of center piece

Sinusoidal depth profile, maximum/minimum at ends Three (3) pieces cut to fit mounting area dimensions

Depth: Maximum @ 236 mm (9.291 in.)

Minimum @ 62 mm (2.441 in.)

Installation: Mounted vertically in square grid pattern, flat edge facing Layer 1

Overall Weight: 12.25 kg (27 lbs)



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2005 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.

THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

An MALION Technical Center

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

Test Report

RALTM-A19-036 Page 2 of 9

TURF 2019-01-25

Physical Measures

Size: 2.74 m (108.0 in) wide by 2.43 m (95.5 in) long

Thickness: 0.25 m (9.893 in) Weight: 32.55 kg (71.75 lbs) Mass per Unit Area: 4.89 kg/m² (1.0 lbs/ft²)

Calculation Area: 6.655 m² (71.63 ft²)

Test Environment

Room Volume: 291.98 m³

Temperature: $21.3 \,^{\circ}\text{C} \pm 0.1 \,^{\circ}\text{C}$ (Requirement: $\geq 10 \,^{\circ}\text{C}$ and $\leq 5 \,^{\circ}\text{C}$ change) Relative Humidity: $65.4 \% \pm 0.6 \%$ (Requirement: $\geq 40 \%$ and $\leq 5 \%$ change)

Barometric Pressure: 99.5 kPa (Requirement not defined)

An MALION Technical Center

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

Test Report

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

> RALTM-A19-036 Page 3 of 9

TURF 2019-01-25





Figure 1 – Specimen mounted in test chamber



Figure 2 – Detail of fissured ceiling tile, typical Switchblade joint



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2005 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

> **RALTM-A19-036** Page 4 of 9


Test Report

An MALION Technical Center

TURF 2019-01-25



Figure 3 – Detail of Switchblade material and chamfered edges



1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

An MALION Technical Center

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

Test Report

RALTM-A19-036

TURF 2019-01-25

Page 5 of 9


MOUNTING METHOD

Type E-400 Mounting: The test specimen was mounted with an airspace behind it. The numeral suffix in the designation is the distance in millimeters from the test surface to the exposed face of the test specimen, rounded to the nearest integer multiple of 5. For the purposes of this report, the mounting designation uses the top face of Layer 1 for reference. Perimeter edges of Layer 1 were sealed with metal framing.

TEST RESULTS

1/3 Octave Center			
Frequency	Total Absorption	Total Absorption	Absorption
(Hz)	(m^2)	(Sabins)	Coefficient
100	4.66	50.13	0.70
** 125	3.70	39.88	0.56
160	3.72	40.03	0.56
200	3.85	41.39	0.58
** 250	4.18	44.99	0.63
315	4.58	49.31	0.69
400	4.72	50.78	0.71
** 500	5.40	58.16	0.81
630	5.71	61.49	0.86
800	6.00	64.58	0.90
** 1000	6.39	68.81	0.96
1250	6.67	71.80	1.00
1600	6.73	72.48	1.01
** 2000	6.70	72.08	1.01
2500	6.70	72.12	1.01
21.50	6.68	71 0 2	1.00
3150	6.67	71.82	1.00
** 4000	6.66	71.67	1.00
5000	6.40	68.94	0.96

SAA = 0.85NRC = 0.85



1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

An MALION Technical Center

Test Report

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

RALTM-A19-036

TURF 2019-01-25

TEST RESULTS (Continued)

The sound absorption average (SAA) is defined in ASTM C423-17 Section 3.1.1 as the average, rounded to the nearest integer multiple of 0.01, of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, expressed to the nearest integer multiple of 0.05.

Tested by

Marc Sciaky

Experimentalist

Report by

Acoustician

Eric P. Wolfram

Laboratory Manager

An MALION Technical Center

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

Test Report


RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

> RALTM-A19-036 Page 7 of 9

TURF 2019-01-25

SOUND ABSORPTION REPORT

Switchblade AF over fissured ceiling tiles



SAA = 0.85NRC = 0.85

TESTING

NYLAP LAB CODE 100227-0

® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NYLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2005 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NYLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.

THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104 An MALION Technical Center

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

Test Report

RALTM-A19-036

Page 8 of 9

TURF 2019-01-25

APPENDIX A: Extended Frequency Range Data

1/2 Octova Dand

Specimen: Switchblade AF over fissured ceiling tiles (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-17, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

1/3 Octave Band		
Center Frequency	Total Absorption	Absorption
(Hz)	(Sabins)	Coefficient
21.5	22.02	0.45
31.5	32.02	0.45
40	45.08	0.63
50	52.76	0.74
63	29.96	0.42
80	59.49	0.83
100	50.13	0.70
125	39.88	0.56
160	40.03	0.56
200	41.39	0.58
250	44.99	0.63
315	49.31	0.69
400	50.78	0.71
500	58.16	0.81
630	61.49	0.86
800	64.58	0.90
1000	68.81	0.96
1250	71.80	1.00
1600	72.48	1.01
2000	72.08	1.01
2500	72.12	1.01
3150	71.82	1.00
4000	71.67	1.00
5000	68.94	0.96
6300	69.16	0.97
8000	68.15	0.95
10000	63.86	0.89
12500	61.70	0.86



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2005 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE

SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE GENEVA, IL 60134 630-232-0104

An MALION Technical Center

RIVERBANK.ALIONSCIENCE.COM FOUNDED 1918 BY WALLACE CLEMENT SABINE

Test Report

RALTM-A19-036

TURF 2019-01-25

Page 9 of 9

APPENDIX B: Instruments of Traceability

Specimen: Switchblade AF over fissured ceiling tiles (See Full Report)

		Serial	Date of	Calibration
Description	Model	<u>Number</u>	Certification	Due
System 1	Type 3160-A-042	3160- 106968	2018-08-09	2019-08-09
Bruel & Kjaer Mic And Preamp A	Type 4943-B-001	2311428	2018-09-28	2019-09-28
Bruel & Kjaer Pistonphone	Type 4228	2781248	2018-08-06	2019-08-06
Omega Digital Temp., Humid. And Pressure Recorder	OM-CP- PRHTemp2000	P97844	2018-02-03	2019-02-03

END

